IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of:

HONG et al.

Application No.: 10/767,858

Filed: January 30, 2004

For: Oxidation Protective Multiple Coating Method for Carbon/Carbon Composites Confirmation No.: 2968

Art Unit: 1792

Braminer: Ngampa, Briget P.

Atty. Docket: 2236.0080000/JUK/SMW

Declaration of Soon Hyung Hong, Yang Ho Bae, Ji Young Song and Hee Yeoun Kim Under 37 C.F.R. § 1.132

Attn: Mail Stop Amendment

Commissioner for Patents PO Box 1450 Alexandria, VA 22313-1450

Sir:

The undersigned Soon Hyung Hong, Yang Ho Bae, Ji Young Song, and Hee Yeoun Kim declare and state as follows:

- We are co-inventors of the invention described in one or more of the pending claims of the captioned application.
- It is our understanding that claim 5 of the captioned application was rejected by
 the Examiner in the Office Action of Pebruary 11, 2008, over Galasso et al. (U.S.
 Pat. No. 4,425,407), Booth et al. (U.S. Pat. No. 5,330,789), Holko et al. (U.S. Pat.
 No. 5,021,107) and Hanzawa et al. (U.S. Pub. No. 2001/051,258).

- It is our understanding that claim 5 as rejected by the Examiner recited: "The
 method of claim 1, wherein the heat-treating in (c) is performed at a temperature
 of about 1400 °C to about 1600 °C under a pressure of about 10 mTorr to about
 1000 mTorr.
- 4. It is our understanding that the features of claim 5 have been incorporated into amended claim 1 in the present Amendment and Reply, and that claim 5 has been cancelled. Amended claim 1 recites: "A method of making an oxidation protective multiple coating for a carbon/carbon composite, the method comprising:
 - forming an initial coating layer in the carbon/carbon composite by a pack comentation process.
 - spraying a mixture comprising a vehicle liquid and Si powder on the carbon/carbon composite,
 - (c) heat-treating at a temperature of 1400 °C to about 1600 °C under a pressure of about 10 mTorr to about 1000 mTorr the Si-coated carbon/carbon composite to impregnate the initial coating layer and cracks in the initial coating layer with Si;
 - thereby forming an SiC layer and an Si layer; and
 - (d) oxidizing the Si layer to form an SiO₂ film."
- The temperature range of the heat treating in (c) is critical, and the considerations for the heat treating include (1) economic cost considerations, and (2) functional

considerations, including the complete and uniform infiltration of the Si on the carbon/carbon composites.

- To minimize the economic costs associated with heat treating, we have found that high temperature processing above 1600 °C is not necessary. This point was identified in the ceptioned application at paragraph [0027].
- 7. Fluidity of Si powder is important in the process of Si infiltration. Solid state Si powder does not have good fluidity, making movement of the Si into carbon/carbon composite pores difficult. Also, in order to be coated, the carbon/carbon composite substrate and Si should react together. Reactions between the carbon/carbon composite and Si are minimal if Si is in a solid state.
- Fluidity of Si is insufficient at 1380 °C, resulting in an imperfect coating as shown in Fig. I.



Fig.1. When infiltration is performed at a low temperature (1380 °C), carbon fiber shows and pores or cracks are not coated perfectly.

- 9. The known melting temperature of Si is 1412 °C. To increase the diffusion speed of the Si into the pores, the temperature should be increased near to or higher than the melting point of Si. In order to investigate temperatures which result in an effective fluidity of Si, heat treating temperatures between 1400 °C ~ 1600 °C were attempted.
- When the heat treating was performed near the melting point (1412 °C), Si
 fluidity increases as shown in Fig. 2 and the Si adheres to the oarbon/carbon
 composite.




Fig. 2. Carbon/carbon composite Si-infiltrated at 1412 °C (melting point).

However, Fig. 2 demonstrates that while Si coats the composite in some areas, other areas contain pores. The pores result from the insufficient fluidity of Si, indicating that the heat treating should occur at a temperature at or above the melting point.

 When the heat treating temperature increased to 1425°C, the carbon/carbon composite was coated uniformly as in Fig. 3.





Fig.3. Carbon/carbon composite Si-infiltrated at 1425 °C

The uniformly coated Si on the carbon/carbon substrate improved oxidation resistance.

 The data presented herein demonstrates the critical nature of heat treating the Sicoated carbon/carbon composite to imprgnate the initial coating layer and cracks in the initial coating later with Si. 13. We hereby declare that all statements made herein of our own knowledge are true, and that all statements made on information and belief are believed to be true; and further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Oct. 22. 248	Goonh Hong	
Date	Soon Hyung Hong	
Date	Yang Ho Bae	
Oct, 22, 2008	Jenes	
Date	Ji Young Song	
Oct . 22 , 2009	when	
Date	Hee Yeolin Kim	

870312_1.DOC

13. We hereby declare that all statements made herein of our own knowledge are true, and that all statements made on information and belief are believed to be true; and further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Date	Soon Hyurig Hong
2008/10/23 Date	Toyo Ho Bas
Date	Ii Young Song
Date	Hee Yeour Kim

870312 1.DOC